



Rapid Automated Induction Lamination (RAIL) for High-Volume Production of Carbon/Thermoplastic Laminates

by Nicholas Shevchenko, Bruce K. Fink, Shridhar Yarlagadda,
John J. Tierney, Dirk Heider, and John W. Gillespie, Jr.

ARL-TR-2478

May 2001

20010611 028

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5069

ARL-TR-2478

May 2001

Rapid Automated Induction Lamination (RAIL) for High-Volume Production of Carbon/Thermoplastic Laminates

Nicholas Shevchenko and Bruce K. Fink

Weapons and Materials Research Directorate, ARL

Shridhar Yarlagaadda, John J. Tierney, Dirk Heider, and
John W. Gillespie, Jr.

University of Delaware

Abstract

An innovative Rapid Automated Induction Lamination (RAIL) process has been developed that can fabricate fully consolidated 8-ply AS4/polyetherimide (PEI) laminates in high volumes. The process relies on induction-based rapid volumetric heating for multilayer consolidation at very rapid rates (less than 30-s cycle times), while maintaining high quality (<1% voids). Full translation of mechanical properties has been achieved in comparison to baseline processes, such as autoclave and vacuum debulk with an order of magnitude increase in throughput. The RAIL process has the potential to be integrated with thermoforming for high-volume production of net-shape carbon/thermoplastic parts.

Acknowledgments

The authors thank the U.S. Army Armaments Research Development and Engineering Center (ARDEC), the Strategic Environmental Research and Development Program (SERDP) Office and the Defense Advanced Research Projects Agency (DARPA) for funding this effort. The authors acknowledge technical contributions from members of the team from Alliant Techsystems (Jack Gerhard, Darin George, Mark Shaffer, Eric Lynam and Jim Condon), ARDEC (John Lutz and George Karshina), the U.S. Army Research Laboratory (ARL) (Chris Hoppel and William Drysdale), and others from the University of Delaware (Lorence Augh for mechanical property testing, and Hee-June Kim for induction modeling efforts).

INTENTIONALLY LEFT BLANK.

Table of Contents

	<u>Page</u>
Acknowledgments.....	iii
List of Figures.....	vii
List of Tables	ix
1. Introduction	1
2. Material System and Process Requirements.....	3
3. Process and Hardware Design	4
3.1 Process Simulation	4
3.2 Induction Design	6
3.3 Hardware Design.....	6
4. Experimental Laminator	6
5. Laminate Performance and Quality	8
6. Potential Applications of Rail Process.....	10
7. Conclusions	11
8. References	13
Distribution List	15
Report Documentation Page.....	33

INTENTIONALLY LEFT BLANK.

List of Figures

<u>Figure</u>	<u>Page</u>
1. Process Schematic for RAIL.....	4
2. Simulation scheme for Parametric Studies, Process, and Hardware Design.....	5
3. Lab-Scale Experimental Laminator to Demonstrate RAIL Process.....	8
4. IR Temperature Profile of Heating Zones in the RAIL Process	9
5. Micrographs Indicating Void Content Comparison Between Vacuum-Debulk Baseline (Left) and Induction-Processed Laminate (Right)	9
6. Process Schematic for an Integrated Laminating and Thermoforming System.....	11

INTENTIONALLY LEFT BLANK.

List of Tables

<u>Table</u>	<u>Page</u>
1. Examples of Process Setpoints and Hardware Parameters Determined by Simulation	7
2. Mechanical Performance of Induction-Processed Laminates	10

INTENTIONALLY LEFT BLANK.

1. Introduction

Carbon fiber-based composites are being used today in a wide range of structural applications in aerospace and defense systems. Material and manufacturing costs have been traditional barriers for use in the automotive and consumer industries. Low-cost carbon fiber is now available that may open markets for these high-volume applications. Carbon fiber-reinforced thermoplastic composites offer economic and performance advantages in terms of low-cycle times, rapid multistep processing (e.g., consolidation, stamping, welding) and high-specific stiffness and strength. Carbon-thermoplastic composites offer the potential for significant weight reduction and recycling benefits.

A key concern in the economics of carbon fiber composites is manufacturing costs, especially for thermoplastic systems. The search for cost-effective manufacturing has led to the study of induction heating for processing of carbon fiber-reinforced thermoplastics. Induction processing offers a potential solution by enabling rapid volumetric heating of the thermoplastic laminae leading to multilayer consolidation. This technology enables reduction in cycle times, while maintaining quality, compared to conventional compression molding processes.

A review of the literature in the area of induction heating and processing of carbon fiber-based composites reveals that the majority of work has focused on heating of preconsolidated laminates. Several efforts [1–9] have focused on using induction as a means for bonding and repair of composites with metal-mesh susceptors or heating elements. Some work has been done [10, 11] on the use of composites on metallic substrates for generation of Joule-loss energy. Little research [12–17] has focused on the use of the inherent conductivity of the carbon fibers for susceptorless heating and bonding.

Border and Salas [12] studied bonding of carbon fiber-reinforced thermoplastic composites by heating the adherends at the joint through the thickness and applying consolidation pressures. Miller et al. [13] and Lin et al. [14] examined induction heating of carbon fiber-reinforced thermoplastics for applications such as die-less forming. They also developed theoretical heating

models, with the conclusion that good electrical contact is required between crossed plies, and Joule heating in the fibers is the heat source. Their work has primarily focused on heating preconsolidated carbon-thermoplastic laminates. An alternative heating mechanism was proposed by Fink et al. [15–18] who observed that, in laminates in which the fibers in adjacent plies do not come into direct electrical contact before or during consolidation, heat generation is caused by dielectric losses in the polymer at the junctions of overlapping fibers from adjacent plies. They also developed theoretical models for unconsolidated laminates, based on the predominate dielectric heating mechanism.

Tests by Miller et al. [13] on cross-ply prepreg stacks resulted in nonuniform heating and consolidation. As their objective was to study induction for forming operations, they concluded that preconsolidated laminates are a better choice of starting material for induction-based thermoforming. Fink et al. [18] extensively tested AS4 carbon fiber/polyetheretherketone-based APC2 consolidated and unconsolidated laminates verifying their models [15–17] for the dominate dielectric heating mechanism in those materials under varying stacking sequences and coil geometries.

The motivation of this work arises from the need to develop an economical and high throughput, carbon-thermoplastic-lamination process capable of obtaining uniform heating for any carbon fiber-based thermoplastic prepreg laminate stack. This requires developing an understanding of the additional mechanism of contact resistance in laminates exhibiting fiber-fiber contact before and during consolidation as developed by Yarlagadda et al. [19] and Kim et al. [20] and incorporated into this work. It also requires developing a manufacturing process that achieves uniformity in heating in the plane and takes advantage of the through-thickness volumetric heating potential of induction. In addition, induction offers internal non-contact heating; the possibility of a moving heat source (the coil); high efficiency; control of the heat generation by coil design; and powerful, portable, and easy-to-operate induction generators.

The technology outlined in this effort arose from the need to fabricate thermoplastic sheets in high volumes for munitions. The sheets are currently fabricated from AS4/polyetherimide (PEI) by conventional technology, starting from the raw material (prepreg) to the final product. One of the critical steps during the fabrication process is the lamination of 8-ply prepreg sheets, which is currently being done by vacuum-debulk tables with 300-s cycle times. Full-scale factory production demands cycle times of less than 20 s with equivalent quality and mechanical properties. For this application, throughputs of 10 ft/min are required. The primary objective of this work was to develop a Rapid Automated Induction Lamination (RAIL) process for high-volume production of carbon fiber-reinforced thermoplastic laminates. Process development, optimization, and hardware design was performed using simulation models accounting for all potential heating mechanisms. A lab-scale machine was fabricated to demonstrate the RAIL process and has successfully fabricated 8-ply laminates from AS4/PEI prepreg at high throughputs. Full translation of mechanical properties was achieved for laminates fabricated using the RAIL process compared to autoclave baselines.

2. Material System and Process Requirements

The RAIL process was developed to fabricate fully consolidated 8-ply laminates of AS4/PEI from prepreg supplied by Cytec Fiberite. Symmetric angle-ply laminates (i.e., $[0/\theta/0/-\theta]_s$, where θ can range from 15° to 90°) were investigated. The prepreg material has an average thickness of 0.0052 in and a fiber volume fraction of approximately 60%.

The requirements of the RAIL process for this specific application were:

- laminate with dimensions of 3 ft (length) and 1 ft (width),
- throughput of 1–10 ft/min,
- void content $<1\%$,
- laminate thickness tolerance ± 2 mil,
- dimensional tolerances (± 35 -mil length, ± 25 -mil width),
- minimal warpage (symmetry),

- maintain fiber orientation and negligible fiber damage or distortion,
- temperature and pressure controls to within desired ranges, and
- automated machine operation.

This criteria was determined such that laminate quality was similar or better than baseline vacuum-debulk or autoclave laminates.

3. Process and Hardware Design

Several process schemes were evaluated as candidates for the RAIL process. The typical design is shown in Figure 1. All of the evaluated schemes had heating and cooling zones; the differences were the heating and cooling mechanisms. In all cases, consolidation was achieved using roller pressure due to the high amplification factor and the short residence times at high throughputs. Process simulations were used to evaluate each process scheme and the design was down-selected based on the desired process requirements.




Figure 1. Process Schematic for RAIL.

3.1 Process Simulation. A complete process simulation was developed that enabled evaluation of various heating and cooling techniques for process design. The simulation was based on and adapted from earlier work on automated tow placement [21, 22] and determined

relationships between input process parameters, such as temperature and pressure profiles and output quality like void content and degree of bonding. A schematic of the process simulation is shown in Figure 2. The temperature solution is generated by a two-dimensional (2-D) transient finite-difference scheme that can handle various types of heat input sources such as infrared (IR), platens, internal heat generation, etc. Transient solutions are necessary since the process is discontinuous and has start/stop zones and process velocities of up to 10 ft/min. Possible boundary conditions include free convection, forced contact (platens), adiabatic, impinging gas, and infrared radiation. The internal heat generation term is based on induction heating in the carbon-fiber prepreg stack.




Figure 2. Simulation Scheme for Parametric Studies, Process, and Hardware Design.

3.2 Induction Design. When directional carbon fiber-based composites are subjected to an alternating magnetic field, volumetric heating of the composite occurs and volumetric heating rates on the order of ~ 100 °C/s have been demonstrated [14–20]. Initial efforts focused on identifying coupled heating mechanisms and induction parameters for uniform heating in the prepreg feedstock [19, 20]. Based on these studies, a rectangular coil design was identified that generated uniform temperature profile across the width of the prepreg stack. Motion of the stack along the feed direction causes the stack to heat up to temperature as it passes through the induction zone.

Based on the temperature solution and pressure profile in each stage of the process, material void content, and degree of bonding were calculated (Figure 2). Details on the process simulation will be published at a later date.

3.3 Hardware Design. For the selected process scheme (Figure 2), parametric studies were performed to identify desired process setpoints and hardware requirements (rollers, platens, etc.) to obtain the desired material quality. Examples of design parameters that were determined using process simulations are shown in Table 1. Note the different setpoints for changing throughput velocities.

4. Experimental Laminator

Based on the simulation models and hardware design, an experimental “proof-of-concept” laminator has been designed and fabricated (Figure 3). The experimental laminator was then rigorously tested to meet the desired requirements. Modifications were made to the stages as required; however, the overall design concept has remained the same.

The laminator is comprised of six stages: (1) infeed, (2) preheat, (3) induction, (4) consolidation, (5) cooling, and (6) outfeed. The infeed rollers align the spot-welded laminate perpendicular to the coil and outfeed rollers. The preheat stage establishes intimate contact

Table 1. Examples of Process Setpoints and Hardware Parameters Determined by Simulation

Hardware Station	Hardware Specification	3 ft/min	6 ft/min	12 ft/min	20 ft/min
Heater Shoe $T_1 = 482\text{ }^{\circ}\text{F}$ $T_1 = 625\text{ }^{\circ}\text{F}$	6 in length Resistance Heaters	505 $^{\circ}\text{F}$ 482 $^{\circ}\text{F}$	610 $^{\circ}\text{F}$ 792 $^{\circ}\text{F}$	939 $^{\circ}\text{F}$ 1180 $^{\circ}\text{F}$	1454 $^{\circ}\text{F}$ 1788 $^{\circ}\text{F}$
Induction Power $T_{\max} = 716\text{ }^{\circ}\text{F}$	1 in wide	3.2 KW	5.7 KW	9.1 KW	12.3 KW
Cooling Shoe	6 in length water cooled	257 $^{\circ}\text{F}$	140 $^{\circ}\text{F}$	77 $^{\circ}\text{F}$	77 $^{\circ}\text{F}$
Consolidation Roller Force $F_{\text{roller}} = 3,200\text{ lb}$	$D_b (F_{\text{shoe}} = 3,200\text{ lb})$	81.08%	89.91%	82.71%	81.60%
	$D_b (F_{\text{shoe}} = 1,600\text{ lb})$	80.01%	89.02%	80.40%	77.52%
	$D_b (F_{\text{shoe}} = 800\text{ lb})$	79.74%	88.61%	79.24%	75.30%
	$V_f (F_{\text{shoe}} = 3,200\text{ lb})$	0.74%	0.76%	1.91%	3.13%
	$V_f (F_{\text{shoe}} = 1,600\text{ lb})$	0.79%	1.24%	2.21%	3.13%
	$V_f (F_{\text{shoe}} = 800\text{ lb})$	0.80%	1.77%	2.47%	3.14%
Consolidation Roller Force $F_{\text{roller}} = 3,200\text{ lb}$	$D_b (F_{\text{shoe}} = 3,200\text{ lb})$	70.55%	79.61%	75.53%	72.88%
	$D_b (F_{\text{shoe}} = 1,600\text{ lb})$	70.54%	78.14%	72.08%	71.12%
	$D_b (F_{\text{shoe}} = 800\text{ lb})$	70.53%	77.43%	70.26%	67.87%
	$V_f (F_{\text{shoe}} = 3,200\text{ lb})$	0.82%	0.76%	1.91%	3.13%
	$V_f (F_{\text{shoe}} = 1,600\text{ lb})$	0.86%	1.24%	2.20%	3.13%
	$V_f (F_{\text{shoe}} = 800\text{ lb})$	0.88%	1.77%	2.47%	3.14%
Consolidation Roller Force $F_{\text{roller}} = 3,200\text{ lb}$	$D_b (F_{\text{shoe}} = 3,200\text{ lb})$	61.20%	71.63%	70.31%	68.52%
	$D_b (F_{\text{shoe}} = 1,600\text{ lb})$	61.18%	69.34%	65.51%	66.42%
	$D_b (F_{\text{shoe}} = 800\text{ lb})$	61.17%	68.18%	62.74%	61.96%
	$V_f (F_{\text{shoe}} = 3,200\text{ lb})$	0.93%	0.76%	1.91%	3.13%
	$V_f (F_{\text{shoe}} = 1,600\text{ lb})$	0.98%	1.24%	2.21%	3.13%
	$V_f (F_{\text{shoe}} = 800\text{ lb})$	1.01%	1.77%	2.47%	3.14%

between plies by heating the outer plies, which aids in heat generation in the induction stage; this is necessary, as intimate contact (surface quality of prepreg) drives the heat-generation capability in the induction stage, and prepreg quality can vary widely. The induction stage generates volumetric heating at high rates ($\sim 100\text{ }^{\circ}\text{C/s}$) and raises the temperature of the material to within the desired process window. An IR-sensor-based feedback control loop is used to maintain temperature to within $\pm 10\text{ }^{\circ}\text{C}$ of the setpoint. The consolidation stage consists of chilled rolls that apply pressure to obtain the desired degree of bonding and void content. The cooling stage reduces the temperature of the laminate to below the glass transition temperature of the polymer.




Figure 3. Lab-Scale Experimental Laminator to Demonstrate RAIL Process.

The outfeed stage is the drive system for the machine and pulls the material through, as well as controls the machine throughput. The laminator is fully automated; once the material feed is accomplished, the stages are automatically lowered and raised as the material goes through at the desired process velocity. A typical thermal profile in the heating zone is shown in Figure 4.

5. Laminate Performance and Quality

Laminator performance was quantified by measurements of void content and tensile properties of the laminate and compared to the vacuum-debulk baseline. Void content measurements for induction-processed laminates showed that voids were primarily in the outer two layers (Figure 5), with almost zero voids in the inner layers (also predicted by the process model). This is due to the chilled consolidation roller that “freezes” the outer two layers and locks in the voids. The inner layers are still at high temperatures and the roller pressure reduces




Figure 4. IR Temperature Profile of Heating Zones in the RAIL Process.




Figure 5. Micrographs Indicating Void Content Comparison Between Vacuum-Debulk Baseline (Left) and Induction-Processed Laminate (Right).

void content. Average void contents were less than 1%. Table 2 shows the measured material properties (American Society for Testing and Materials [ASTM] tests) for various laminates comparing the effect of different processing techniques and cycle times. The induction-processed laminates show identical properties to the vacuum-debulk baseline with an order of magnitude decrease in cycle time.

Table 2. Mechanical Performance of Induction-Processed Laminates

Process	Longitudinal Tensile Strength (ksi)	Longitudinal Tensile Modulus (msi)	Transverse Tensile Strength (ksi)	Transverse Tensile Modulus (msi)	Cycle Time (s)
Vacuum Debulk	191.7 ± 7.1	13.3 ± 0.5	16.3 ± 1.1	1.45 ± 0.04	300
Laminator at 5 ft/min	182.4 ± 2.8	13.6 ± 0.3	16.5 ± 0.3	1.50 ± 0.03	36

Technology developed and proven in the lab-scale laminator is currently being transitioned to a production line at Alliant TechSystems. Lessons learned during the laminator design, fabrication and prove-out have been implemented as part of the design criteria for the factory floor laminator.

6. Potential Applications of RAIL Process

The experimental laminator has demonstrated the high-volume lamination capability of the RAIL process, while maintaining material quality. The RAIL process can be modified to include a thermoforming station for high-volume production of molded parts (Figure 6). The forming station uses cooled dies to rapidly form the part as the material exits the heating zone of the laminator and also cool the part at the same time.

In this design, speed of the forming step determines final throughput. As an example, at 12 ft/min, a 3-ft-long laminate "blank" can be produced in 15 s and if the stamping or forming process is just as fast, throughputs of 4 parts per minute (parts/min) can be achieved. The cycle time of 15 s compares favorably with metal-stamping operations, where times are on the order of 5 s/part. Stamped or formed parts can be fabricated for a variety of process conditions and low-cost carbon preforms, such as woven fabrics, comingled fabric, etc. Of particular interest are




Figure 6. Process Schematic for an Integrated Laminating and Thermoforming System.

fiber preforms that have some axial extendibility since these are well suited for rapid forming of complex shapes. Key parameters are forming die temperatures, die pressures required during forming, and cycle times. It is expected that this design can reduce cycle times and costs of the final part significantly compared to conventional thermoforming.

The experimental laminator currently operates in the discontinuous feed mode where the input material is a 36-in-long \times 12-in-wide 8-ply prepreg stack. The laminator can also operate in a continuous mode, where the 12-in-wide prepreg stack is fed continuously and cut into the desired lengths after laminating. However, preform-handling issues differ significantly for both cases and need to be addressed.

7. Conclusions

An innovative RAIL process has been developed and demonstrated for high-volume production of 8-ply AS4/PEI laminates. The process takes advantage of suscepterless induction heating to generate the volumetric heating necessary for rapid multilayer consolidation for high throughputs. Process models were developed and used for hardware design and fabrication of a proof-of-concept laminator. High-quality laminates have been fabricated at rates from 3–10 ft/min. Cycle times of 20 s have been demonstrated that represents a 15-fold reduction

over the baseline technology. Full translation of mechanical properties has been demonstrated. The RAIL process can be adapted for use with thermoforming technology for high-volume production of net-shape parts. Higher rates can be achieved and will require higher power-induction generators and suitable redesign of hardware elements using the process models.

8. References

1. Benatar, A., and T. G. Gutowski. "Methods for Fusion Bonding Thermoplastic Composites." *SAMPE Quarterly*, vol. 18, no. 1, p. 34, 1986.
2. Nagumo, T., H. Makamura, Y. Yoshida, and K. Hiraoka. "Evaluation of PEEK Matrix Composites." *Proceedings of 32nd International SAMPE Symposium*, 1987.
3. Buckley, J. D., R. L. Fox, and J. R. Tyeryar. "Seam Bonding of Graphite Reinforced Composite Panels." *NASA Advanced Composites Conference*, 1986.
4. Lewis, C. F. "Materials Keep a Low Profile." *Materials Engineering*, issue no. 105, 1988.
5. Buckley J. D., and R. L. Fox. "Rapid Electromagnetic Induction Bonding of Composites, Plastics, and Metals." *Materials Research Society Symposium*, vol.124, Boston, MA, 1988.
6. Lawless G. W., and T. J. Reinhart. "Study of the Induction Heating of Organic Composites." *Proceedings of International SAMPE Conference*, Toronto, Canada, October 1992.
7. Wedgewood, A. R., and P. E. Hardy. "Induction Welding of Thermoset Composite Adherends Using Thermoplastic Interlayers and Susceptors." *Proceedings International SAMPE Conference*, vol. 28, Seattle, WA, November 1996.
8. Fink, B. K., S. Yarlagadda, and J. W. Gillespie, Jr. "Design of a Resistive Susceptor for Uniform Heating During Induction Bonding of Composites." ARL-TR-2148, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, January 2000.
9. Fink, B. K., S. H. McKnight, J. W. Gillespie, Jr., and S. Yarlagadda. "Ferromagnetic Nano-Particulate and Conductive Mesh Susceptors for Induction-Based Repair of Composites." 21st Army Science Conference, Norfolk, VA, June 15-17, 1998.
10. Karamuk, E., E. D. Wetzel, and J. W. Gillespie, Jr. "Modeling and Design of Induction Bonding Process for Infrastructure Rehabilitation with Composite Materials." *Proceedings of Society of Plastics Engineers ANTEC '95*, Boston, MA 1995.
11. Bourbon, P. E., E. Karamuk, R. C. Don, and J. W. Gillespie, Jr. "Induction Heating for Rehabilitation of Steel Structures Using Composites." *ASCE Materials and Methods for Repair*, San Diego, CA, pp. 287-294, 1994.
12. Border J., and R. Salas. "Induction Heated Joining of Thermoplastic Composites Without Metal Susceptors." *34th SAMPE Symposium*, vol. 34, p. 2569, 1989.

13. Miller, A. K., C. Chang, A. Payne, M. Gur, E. Menzel, and A. Peled. "The Nature of Induction Heating in Graphite Fiber, Polymer Matrix Composite Materials." *SAMPE Journal*, vol. 26, no. 4, p. 37, 1996.
14. Lin, W., A. K. Miller, and O. Buneman. "Predictive Capabilities of an Induction Heating Model for Complex-Shape Graphite Fiber/Polymer Matrix Composites." *24th International SAMPE Technical Conference*, vol. 24, p. 606, 20–22 October 1992.
15. Fink, B. K., R. L. McCullough, and J. W. Gillespie, Jr. "A Local Theory of Heating in Cross-Ply Carbon Fiber Thermoplastic Composites by Magnetic Induction." *Polymer Engineering and Science*, vol. 32, no. 5, pp. 357–369, 1992.
16. Fink, B. K., R. L. McCullough, and J. W. Gillespie, Jr. "A Model to Predict the Planar Electrical Potential Distribution in Cross-Ply Carbon-Fiber Composites Subjected to Alternating Magnetic Fields." *Composites Science and Technology*, vol. 49, no. 1, pp. 71–80, 1993.
17. Fink, B. K., R. L. McCullough, and J. W. Gillespie, Jr. "A Model to Predict the Through-Thickness Distribution of Heat Generation in Cross-Ply Carbon-Fiber Composites Subjected to Alternating Magnetic Fields." *Composites Science and Technology*, vol. 55, no. 2, pp. 119–130, 1995.
18. Fink, B. K., J. W. Gillespie, Jr., and R. L. McCullough. "Experimental Verification of Models for Induction Heating of Continuous-Carbon-Fiber Composites." *Polymer Composites*, vol. 17, no. 2, pp. 198–209, 1996.
19. Yarlagadda, S., H. J. Kim, J. W. Gillespie, Jr., N. Shevchenko, and B. K. Fink. "Heating Mechanisms in Induction Processing of Carbon Thermoplastic Prepreg." *Proceedings of 45th International SAMPE Symposium and Exhibition*, p. 79, Long Beach, CA, 21 May 2000.
20. Kim, H. J., S. Yarlagadda, J. W. Gillespie, Jr., N. Shevchenko, and B. K. Fink. "A Study on the Induction Heating of Carbon Fiber Reinforced Thermoplastic Composites." Ninth U.S.–Japan Conference on Composite Materials, July 2000.
21. Butler, C. A., R. Pitchumani, R. L. McCullough, and A. R. Wedgewood. "Coupled Effects of Healing and Intimate Contact During Thermoplastic Fusion Bonding." *10th ASM/ESD Advanced Composites Conference*, pp. 595–604, 7–10 November 1994.
22. Tierney, J. J., R. F. Eduljee, and J. W. Gillespie, Jr. "Material Response During Robotic Tow Placement of Thermoplastic Composites." *Proceedings of the 11th Annual ASM/ESD Advanced Composites Conference*, pp. 315–329, November 1995.

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	DEFENSE TECHNICAL INFORMATION CENTER DTIC OCA 8725 JOHN J KINGMAN RD STE 0944 FT BELVOIR VA 22060-6218
1	HQDA DAMO FDT 400 ARMY PENTAGON WASHINGTON DC 20310-0460
1	OSD OUSD(A&T)/ODDR&E(R) DR R J TREW 3800 DEFENSE PENTAGON WASHINGTON DC 20301-3800
1	COMMANDING GENERAL US ARMY MATERIEL CMD AMCRDA TF 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001
1	INST FOR ADVNCD TCHNLGY THE UNIV OF TEXAS AT AUSTIN 3925 W BRAKER LN STE 400 AUSTIN TX 78759-5316
1	DARPA SPECIAL PROJECTS OFFICE J CARLINI 3701 N FAIRFAX DR ARLINGTON VA 22203-1714
1	US MILITARY ACADEMY MATH SCI CTR EXCELLENCE MADN MATH MAJ HUBER THAYER HALL WEST POINT NY 10996-1786
1	DIRECTOR US ARMY RESEARCH LAB AMSRL D DR D SMITH 2800 POWDER MILL RD ADELPHI MD 20783-1197

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DIRECTOR US ARMY RESEARCH LAB AMSRL CI AI R 2800 POWDER MILL RD ADELPHI MD 20783-1197
3	DIRECTOR US ARMY RESEARCH LAB AMSRL CI LL 2800 POWDER MILL RD ADELPHI MD 20783-1197
3	DIRECTOR US ARMY RESEARCH LAB AMSRL CI IS T 2800 POWDER MILL RD ADELPHI MD 20783-1197
	<u>ABERDEEN PROVING GROUND</u>
2	DIR USARL AMSRL CI LP (BLDG 305)

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DIRECTOR US ARMY RESEARCH LAB AMSRL CP CA D SNIDER 2800 POWDER MILL RD ADELPHI MD 20783-1145
1	DIRECTOR US ARMY RESEARCH LAB AMSRL OP SD TA 2800 POWDER MILL RD ADELPHI MD 20783-1145
3	DIRECTOR US ARMY RESEARCH LAB AMSRL OP SD TL 2800 POWDER MILL RD ADELPHI MD 20783-1145
1	DIRECTOR US ARMY RESEARCH LAB AMSRL CI IS T 2800 POWDER MILL RD ADELPHI MD 20783-1145
1	DIRECTOR DA OASARDA SARD SO 103 ARMY PENTAGON WASHINGTON DC 20310-0103
1	DPTY ASST SECY FOR R&T SARD TT THE PENTAGON RM 3EA79 WASHINGTON DC 20301-7100
1	COMMANDER US ARMY MATERIEL CMD AMXMI INT 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001
4	COMMANDER US ARMY ARDEC AMSTA AR CC G PAYNE J GEHBAUER C BAULIEU H OPAT PICATINNY ARSENAL NJ 07806-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	COMMANDER US ARMY ARDEC AMSTA AR AE WW E BAKER J PEARSON PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR TD C SPINELLI PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR FSE PICATINNY ARSENAL NJ 07806-5000
6	COMMANDER US ARMY ARDEC AMSTA AR CCH A W ANDREWS S MUSALLI R CARR M LUCIANO E LOGSDEN T LOUZEIRO PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR CCH P J LUTZ PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR FSF T C LIVECCHIA PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR QAC T C C PATEL PICATINNY ARSENAL NJ 07806-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	COMMANDER US ARMY ARDEC AMSTA AR M D DEMELLA PICATINNY ARSENAL NJ 07806-5000
3	COMMANDER US ARMY ARDEC AMSTA AR FSA A WARNASH B MACHAK M CHIEFA PICATINNY ARSENAL NJ 07806-5000
2	COMMANDER US ARMY ARDEC AMSTA AR FSP G M SCHIKSNIS D CARLUCCI PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR FSP A P KISATSKY PICATINNY ARSENAL NJ 07806-5000
2	COMMANDER US ARMY ARDEC AMSTA AR CCH C H CHANIN S CHICO PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA ASF PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR WET T SACHAR BLDG 172 PICATINNY ARSENAL NJ 07806-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
9	COMMANDER US ARMY ARDEC AMSTA AR CCH B P DONADIA F DONLON P VALENTI C KNUTSON G EUSTICE S PATEL G WAGNECZ R SAYER F CHANG PICATINNY ARSENAL NJ 07806-5000
6	COMMANDER US ARMY ARDEC AMSTA AR CCL F PUZYCKI R MCHUGH D CONWAY E JAROSZEWSKI R SCHLENNER M CLUNE PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR QAC T D RIGOGLIOSO PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR SRE D YEE PICATINNY ARSENAL NJ 07806-5000
1	US ARMY ARDEC INTELLIGENCE SPECIALIST AMSTA AR WEL F M GUERRIERE PICATINNY ARSENAL NJ 07806-5000
2	PEO FIELD ARTILLERY SYS SFAE FAS PM H GOLDMAN T MCWILLIAMS PICATINNY ARSENAL NJ 07806-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
11	PM TMAS SFAE GSSC TMA R MORRIS C KIMKER D GUZOWICZ E KOPACZ R ROESER R DARCY R MCDANOLDS L D ULISSE C ROLLER J MCGREEN B PATTTER PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC AMSTA AR WEA J BRESCIA PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY ARDEC PRODUCTION BASE MODERN ACTY AMSMC PBM K PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY TACOM PM ABRAMS SFAE ASM AB 6501 ELEVEN MILE RD WARREN MI 48397-5000
6	PM SADARM SFAE GCSS SD COL B ELLIS M DEVINE R KOWALSKI W DEMASSI J PRITCHARD S HROWNAK PICATINNY ARSENAL NJ 07806-5000
1	COMMANDER US ARMY TACOM AMSTA SF WARREN MI 48397-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
3	COMMANDER US ARMY TACOM PM TACTICAL VEHICLES SFAE TVL SFAE TVM SFAE TVH 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM PM BFVS SFAE ASM BV 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM PM AFAS SFAE ASM AF 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	COMMANDER US ARMY TACOM PM RDT&E SFAE GCSS W AB J GODELL 6501 ELEVEN MILE RD WARREN MI 48397-5000
2	COMMANDER US ARMY TACOM PM SURV SYS SFAE ASM SS T DEAN SFAE GCSS W GSI M D COCHRAN 6501 ELEVEN MILE RD WARREN MI 48397-5000
1	US ARMY CERL R LAMPO 2902 NEWMARK DR CHAMPAIGN IL 61822
1	COMMANDER US ARMY TACOM PM SURVIVABLE SYSTEMS SFAE GCSS W GSI H M RYZYI 6501 ELEVEN MILE RD WARREN MI 48397-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	COMMANDER US ARMY TACOM PM BFV SFAE GCSS W BV S DAVIS 6501 ELEVEN MILE RD WARREN MI 48397-5000	1	COMMANDER WATERVLIET ARSENAL SMCWV SPM T MCCLOSKEY BLDG 253 WATERVLIET NY 12189-4050
1	COMMANDER US ARMY TACOM PM LIGHT TACTICAL VHCLS AMSTA TR S A J MILLS MS 209 6501 ELEVEN MILE RD WARREN MI 48397-5000	2	TSM ABRAMS ATZK TS S JABURG W MEINSHAUSEN FT KNOX KY 40121
1	COMMANDER US ARMY TACOM CHIEF ABRAMS TESTING SFAE GCSS W AB QT T KRASKIEWICZ 6501 ELEVEN MILE RD WARREN MI 48397-5000	3	ARMOR SCHOOL ATZK TD R BAUEN J BERG A POMEY FT KNOX KY 40121
15	COMMANDER US ARMY TACOM AMSTA TR R J CHAPIN R MCCLELLAND D THOMAS J BENNETT D HANSEN AMSTA JSK S GOODMAN J FLORENCE K IYER D TEMPLETON A SCHUMACHER AMSTA TR D D OSTBERG L HINOJOSA B RAJU AMSTA CS SF H HUTCHINSON F SCHWARZ WARREN MI 48397-5000	11	BENET LABORATORIES AMSTA AR CCB R FISCELLA G D ANDREA E KATHE M SCAVULO G SPENCER P WHEELER K MINER J VASILAKIS G FRIAR R HASENBEIN AMSTA CCB R S SOPOK WATERVLIET NY 12189-4050
1	COMMANDER WATERVLIET ARSENAL SMCWV QAE Q B VANINA BLDG 44 WATERVLIET NY 12189-4050	2	HQ IOC TANK AMMUNITION TEAM AMSIO SMT R CRAWFORD W HARRIS ROCK ISLAND IL 61299-6000
		2	DAVID TAYLOR RESEARCH CTR R ROCKWELL W PHYLLAIER BETHESDA MD 20054-5000
		2	COMMANDER US ARMY AMCOM AVIATION APPLIED TECH DIR J SCHUCK FT EUSTIS VA 23604-5577

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DIRECTOR US ARMY AMCOM SFAE AV RAM TV D CALDWELL BLDG 5300 REDSTONE ARSENAL AL 35898	1	NAVAL SURFACE WARFARE CTR DAHLGREN DIV CODE G06 DAHLGREN VA 22448
2	US ARMY CORPS OF ENGINEERS CERD C T LIU CEW ET T TAN 20 MASS AVE NW WASHINGTON DC 20314	1	NAVAL SURFACE WARFARE CTR TECH LIBRARY CODE 323 17320 DAHLGREN RD DAHLGREN VA 22448
1	US ARMY COLD REGIONS RSCH & ENGRNG LAB P DUTTA 72 LYME RD HANOVER NH 03755	1	NAVAL SURFACE WARFARE CTR CRANE DIVISION M JOHNSON CODE 20H4 LOUISVILLE KY 40214-5245
1	SYSTEM MANAGER ABRAMS ATZK TS LTC J H NUNN BLDG 1002 RM 110 FT KNOX KY 40121	8	DIRECTOR US ARMY NATIONAL GROUND INTELLIGENCE CTR D LEITER M HOLTUS M WOLFE S MINGLEDORF J GASTON W GSTATTENBAUER R WARNER J CRIDER 220 SEVENTH ST NE CHARLOTTESVILLE VA 22091
1	USA SBCCOM PM SOLDIER SPT AMSSB PM RSS A J CONNORS KANSAS ST NATICK MA 01760-5057	6	US ARMY SBCCOM SOLDIER SYSTEMS CENTER BALLISTICS TEAM J WARD MARINE CORPS TEAM J MACKIEWICZ BUS AREA ADVOCACY TEAM W HASKELL SSCNC WST W NYKVIST T MERRILL S BEAUDOIN KANSAS ST NATICK MA 01760-5019
3	BALLISTICS TEAM AMSSB RIP PHIL CUNNIFF JOHN SONG WALTER ZUKAS KANSAS ST NATICK MA 01760-5057	3	NAVAL RESEARCH LAB I WOLOCK CODE 6383 R BADALIANCE CODE 6304 L GAUSE WASHINGTON DC 20375
2	MATERIAL SCIENCE TEAM AMSSB RSS JEAN HERBERT MICHAEL SENNETT KANSAS ST NATICK MA 01760-5057	2	NAVAL SURFACE WARFARE CTR U SORATHIA C WILLIAMS CD 6551 9500 MACARTHUR BLVD WEST BETHESDA MD 20817
2	OFC OF NAVAL RESEARCH D SIEGEL CODE 351 J KELLY 800 N QUINCY ST ARLINGTON VA 22217-5660		

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
9	US ARMY RESEARCH OFC A CROWSON J CHANDRA H EVERETT J PRATER R SINGLETON G ANDERSON D STEPP D KISEROW J CHANG PO BOX 12211 RESEARCH TRIANGLE PARK NC 27709-2211	1	AFRL MLBC 2941 P ST RM 136 WRIGHT PATTERSON AFB OH 45433-7750
2	COMMANDER NAVAL SURFACE WARFARE CTR CARDEROCK DIVISION R PETERSON CODE 2020 M CRITCHFIELD CODE 1730 BETHESDA MD 20084	1	AFRL MLSS R THOMSON 2179 12TH ST RM 122 WRIGHT PATTERSON AFB OH 45433-7718
8	NAVAL SURFACE WARFARE CTR J FRANCIS CODE G30 D WILSON CODE G32 R D COOPER CODE G32 J FRAYSSE CODE G33 E ROWE CODE G33 T DURAN CODE G33 L DE SIMONE CODE G33 R HUBBARD CODE G33 DAHLGREN VA 22448	2	AFRL F ABRAMS J BROWN BLDG 653 2977 P ST STE 6 WRIGHT PATTERSON AFB OH 45433-7739
1	NAVAL SEA SYSTEMS CMD D LIESE 2531 JEFFERSON DAVIS HWY ARLINGTON VA 22242-5160	1	AFRL MLS OL L COULTER 7278 4TH ST BLDG 100 BAY D HILL AFB UT 84056-5205
1	NAVAL SURFACE WARFARE CTR M LACY CODE B02 17320 DAHLGREN RD DAHLGREN VA 22448	1	OSD JOINT CCD TEST FORCE OSD JCCD R WILLIAMS 3909 HALLS FERRY RD VICKSBURG MS 29180-6199
2	NAVAL SURFACE WARFARE CTR CARDEROCK DIVISION R CRANE CODE 2802 C WILLIAMS CODE 6553 3A LEGGETT CIR BETHESDA MD 20054-5000	1	DEFENSE NUCLEAR AGENCY INNOVATIVE CONCEPTS DIV 6801 TELEGRAPH RD ALEXANDRIA VA 22310-3398
1	EXPEDITIONARY WARFARE DIV N85 F SHOUP 2000 NAVY PENTAGON WASHINGTON DC 20350-2000	1	WATERWAYS EXPERIMENT D SCOTT 3909 HALLS FERRY RD SC C VICKSBURG MS 39180
		5	DIRECTOR LLNL R CHRISTENSEN S DETERESA F MAGNESS M FINGER MS 313 M MURPHY L 282 PO BOX 808 LIVERMORE CA 94550

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
3	DARPA M VANFOSSEN S WAX L CHRISTODOULOU 3701 N FAIRFAX DR ARLINGTON VA 22203-1714	1	OAK RIDGE NATIONAL LABORATORY C EBERLE MS 8048 PO BOX 2008 OAK RIDGE TN 37831
2	FAA TECH CENTER P SHYPRYKEVICH AAR 431 ATLANTIC CITY NJ 08405	1	OAK RIDGE NATIONAL LABORATORY C D WARREN MS 8039 PO BOX 2008 OAK RIDGE TN 37831
2	SERDP PROGRAM OFC PM P2 C PELLERIN B SMITH 901 N STUART ST STE 303 ARLINGTON VA 22203	7	NIST R PARNAS J DUNKERS M VANLANDINGHAM MS 8621 J CHIN MS 8621 D HUNSTON MS 8543 J MARTIN MS 8621 D DUTHINH MS 8611 100 BUREAU DR GAITHERSBURG MD 20899
1	FAA MIL HDBK 17 CHAIR L ILCEWICZ 1601 LIND AVE SW ANM 115N RESTON VA 98055	1	HYDROGEOLOGIC INC SERDP ESTCP SPT OFC S WALSH 1155 HERNDON PKWY STE 900 HERNDON VA 20170
1	US DEPT OF ENERGY OFC OF ENVIRONMENTAL MANAGEMENT P RITZCOVAN 19901 GERMANTOWN RD GERMANTOWN MD 20874-1928	3	NASA LANGLEY RSCH CTR AMSRL VS W ELBER MS 266 F BARTLETT JR MS 266 G FARLEY MS 266 HAMPTON VA 23681-0001
1	DIRECTOR LLNL F ADDESSIO MS B216 PO BOX 1633 LOS ALAMOS NM 87545	1	NASA LANGLEY RSCH CTR T GATES MS 188E HAMPTON VA 23661-3400
1	OAK RIDGE NATIONAL LABORATORY R M DAVIS PO BOX 2008 OAK RIDGE TN 37831-6195	1	FHWA E MUNLEY 6300 GEORGETOWN PIKE MCLEAN VA 22101
3	DIRECTOR SANDIA NATIONAL LABS APPLIED MECHANICS DEPT MS 9042 J HANDROCK Y R KAN J LAUFFER PO BOX 969 LIVERMORE CA 94551-0969	4	CYTEC FIBERITE R DUNNE D KOHLI M GILLIO R MAYHEW 1300 REVOLUTION ST HAVRE DE GRACE MD 21078

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	USDOT FEDERAL RAILRD M FATEH RDV 31 WASHINGTON DC 20590	2	COMPOSIX D BLAKE L DIXON 120 O NEILL DR HEBRUN OH 43025
1	CENTRAL INTLLGNC AGNCY OTI WDAG GT W L WALTMAN PO BOX 1925 WASHINGTON DC 20505	2	SIMULA J COLTMAN R HUYETT 10016 S 51ST ST PHOENIX AZ 85044
1	MARINE CORPS INTLLGNC ACTVTY D KOSITZKE 3300 RUSSELL RD STE 250 QUANTICO VA 22134-5011	1	SIOUX MFG B KRIEL PO BOX 400 FT TOTTEN ND 58335
1	DIRECTOR NATIONAL GRND INTLLGNC CTR IANG TMT 220 SEVENTH ST NE CHARLOTTESVILLE VA 22902-5396	2	PROTECTION MATERIALS INC M MILLER F CRILLEY 14000 NW 58 CT MIAMI LAKES FL 33014
1	DIRECTOR DEFENSE INTLLGNC AGNCY TA 5 K CRELLING WASHINGTON DC 20310	3	FOSTER MILLER J J GASSNER M ROYLANCE W ZUKAS 195 BEAR HILL RD WALTHAM MA 02354-1196
1	ADVANCED GLASS FIBER YARNS T COLLINS 281 SPRING RUN LANE STE A DOWNINGTON PA 19335	1	ROM DEVELOPMENT CORP R O MEARA 136 SWINEBURNE ROW BRICK MARKET PLACE NEWPORT RI 02840
1	COMPOSITE MATERIALS INC D SHORTT 19105 63 AVE NE PO BOX 25 ARLINGTON WA 98223	2	TEXTRON SYSTEMS T FOLTZ M TREASURE 201 LOWELL ST WILMINGTON MA 08870-2941
1	JPS GLASS L CARTER PO BOX 260 SLATER RD SLATER SC 29683	1	GLCC INC J RAY 103 TRADE ZONE DR STE 26C WEST COLUMBIA SC 29170
1	COMPOSITE MATERIALS INC R HOLLAND 11 JEWEL CT ORINDA CA 94563	1	O GARA HESS & EISENHARDT M GILLESPIE 9113 LESAINTE DR FAIRFIELD OH 45014
1	COMPOSITE MATERIALS INC C RILEY 14530 S ANSON AVE SANTA FE SPRINGS CA 90670		

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	MILLIKEN RSCH CORP H KUHN M MACLEOD PO BOX 1926 SPARTANBURG SC 29303	1	SAIC G CHRYSSOMALLIS 3800 W 80TH ST STE 1090 BLOOMINGTON MN 55431
1	CONNEAUGHT INDUSTRIES INC J SANTOS PO BOX 1425 COVENTRY RI 02816	1	AAI CORPORATION T G STASTNY PO BOX 126 HUNT VALLEY MD 21030-0126
2	BATTELLE NATICK OPNS J CONNORS B HALPIN 209 W CENTRAL ST STE 302 NATICK MA 01760	1	APPLIED COMPOSITES W GRISCH 333 NORTH SIXTH ST ST CHARLES IL 60174
1	ARMTEC DEFENSE PRODUCTS S DYER 85 901 AVE 53 PO BOX 848 COACHELLA CA 92236	3	ALLIANT TECHSYSTEMS INC J CONDON E LYNAM J GERHARD WV01 16 STATE RT 956 PO BOX 210 ROCKET CENTER WV 26726-0210
3	PACIFIC NORTHWEST LAB M SMITH G VAN ARSDALE R SHIPPELL PO BOX 999 RICHLAND WA 99352	1	CUSTOM ANALYTICAL ENG SYS INC A ALEXANDER 13000 TENSOR LANE NE FLINTSTONE MD 21530
8	ALLIANT TECHSYSTEMS INC C CANDLAND MN11 2830 C AAKHUS MN11 2830 B SEE MN11 2439 N VLAHAKUS MN11 2145 R DOHRN MN11 2830 S HAGLUND MN11 2439 M HISSONG MN11 2830 D KAMDAR MN11 2830 600 SECOND ST NE HOPKINS MN 55343-8367	1	OFC DEPUTY UNDER SEC DEFNS JAMES THOMPSON 1745 JEFFERSON DAVIS HWY CRYSTAL SQ 4 STE 501 ARLINGTON VA 22202
2	AMOCO PERFORMANCE PRODUCTS M MICHNO JR J BANISAUKAS 4500 MCGINNIS FERRY RD ALPHARETTA GA 30202-3944	1	PROJECTILE TECHNOLOGY INC 515 GILES ST HAVRE DE GRACE MD 21078
1	SAIC M PALMER 1410 SPRING HILL RD STE 400 MS SH4 5 MCLEAN VA 22102	5	AEROJET GEN CORP D PILLASCH T COULTER C FLYNN D RUBAREZUL M GREINER 1100 WEST HOLLYVALE ST AZUSA CA 91702-0296
		3	HEXCEL INC R BOE PO BOX 18748 SALT LAKE CITY UT 84118

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	HERCULES INC HERCULES PLAZA WILMINGTON DE 19894	2	CYTEC FIBERITE M LIN W WEB 1440 N KRAEMER BLVD ANAHEIM CA 92806
1	BRIGS COMPANY J BACKOFEN 2668 PETERBOROUGH ST HERNDON VA 22071-2443	1	HEXCEL T BITZER 11711 DUBLIN BLVD DUBLIN CA 94568
1	ZERNOW TECHNICAL SERVICES L ZERNOW 425 W BONITA AVE STE 208 SAN DIMAS CA 91773	1	BOEING R BOHLMANN PO BOX 516 MC 5021322 ST LOUIS MO 63166-0516
2	OLIN CORPORATION FLINCHBAUGH DIV E STEINER B STEWART PO BOX 127 RED LION PA 17356	2	BOEING DFNSE & SPACE GP W HAMMOND S 4X55 J RUSSELL S 4X55 PO BOX 3707 SEATTLE WA 98124-2207
1	OLIN CORPORATION L WHITMORE 10101 NINTH ST NORTH ST PETERSBURG FL 33702	2	BOEING ROTORCRAFT P MINGURT P HANDEL 800 B PUTNAM BLVD WALLINGFORD PA 19086
1	GKN AEROSPACE D OLDS 15 STERLING DR WALLINGFORD CT 06492	1	BOEING DOUGLAS PRODUCTS DIV L J HART SMITH 3855 LAKEWOOD BLVD D800 0019 LONG BEACH CA 90846-0001
5	SIKORSKY AIRCRAFT G JACARUSO T CARSTENSAN B KAY S GARBO MS S330A J ADELMANN 6900 MAIN ST PO BOX 9729 STRATFORD CT 06497-9729	1	LOCKHEED MARTIN S REEVE 8650 COBB DR D 73 62 MZ 0648 MARIETTA GA 30063-0648
1	PRATT & WHITNEY C WATSON 400 MAIN ST MS 114 37 EAST HARTFORD CT 06108	1	LOCKHEED MARTIN SKUNK WORKS D FORTNEY 1011 LOCKHEED WAY PALMDALE CA 93599-2502
1	AEROSPACE CORP G HAWKINS M4 945 2350 E EL SEGUNDO BLVD EL SEGUNDO CA 90245	1	LOCKHEED MARTIN R FIELDS 1195 IRWIN CT WINTER SPRINGS FL 32708

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	MATERIALS SCIENCES CORP B W ROSEN 500 OFC CENTER DR STE 250 FT WASHINGTON PA 19034	2	GDLS D REES M PASIK PO BOX 2074 WARREN MI 48090-2074
1	UDLP D MARTIN PO BOX 359 SANTA CLARA CA 95052	1	GDLS MUSKEGON OPERATIONS W SOMMERS JR 76 GETTY ST MUSKEGON MI 49442
1	NORTHROP GRUMMAN CORP ELECTRONIC SENSORS & SYSTEMS DIV E SCHOCH MS V 16 1745A W NURSERY RD LINTHICUM MD 21090	1	GENERAL DYNAMICS AMPHIBIOUS SYS SURVIVABILITY LEAD G WALKER 991 ANNAPOLIS WAY WOODBIDGE VA 22191
2	NORTHROP GRUMMAN ENVIRONMENTAL PROGRAMS R OSTERMAN A YEN 8900 E WASHINGTON BLVD PICO RIVERA CA 90660	6	INST FOR ADVANCED TECH H FAIR I MCNAB P SULLIVAN S BLESS W REINECKE C PERSAD 3925 W BRAKER LN STE 400 AUSTIN TX 78759-5316
1	UDLP G THOMAS PO BOX 58123 SANTA CLARA CA 95052		
2	UDLP R BARRETT MAIL DROP M53 V HORVATICH MAIL DROP M53 328 W BROKAW RD SANTA CLARA CA 95052-0359	2	CIVIL ENGR RSCH FOUNDATION PRESIDENT H BERNSTEIN R BELLE 1015 15TH ST NW STE 600 WASHINGTON DC 20005
3	UDLP GROUND SYSTEMS DIVISION M PEDRAZZI MAIL DROP N09 A LEE MAIL DROP N11 M MACLEAN MAIL DROP N06 1205 COLEMAN AVE SANTA CLARA CA 95052	1	ARROW TECH ASSO 1233 SHELBURNE RD STE D8 SOUTH BURLINGTON VT 05403-7700
4	UDLP R BRYNSVOLD P JANKE MS 170 4800 EAST RIVER RD MINNEAPOLIS MN 55421-1498	1	R EICHELBERGER CONSULTANT 409 W CATHERINE ST BEL AIR MD 21014-3613
1	GDLS DIVISION D BARTLE PO BOX 1901 WARREN MI 48090	1	UCLA MANE DEPT ENGR IV H T HAHN LOS ANGELES CA 90024-1597

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	UNIV OF DAYTON RESEARCH INST R Y KIM A K ROY 300 COLLEGE PARK AVE DAYTON OH 45469-0168
1	MIT P LAGACE 77 MASS AVE CAMBRIDGE MA 01887
1	IIT RESEARCH CENTER D ROSE 201 MILL ST ROME NY 13440-6916
1	GA TECH RSCH INST GA INST OF TCHNLGY P FRIEDERICH ATLANTA GA 30392
1	MICHIGAN ST UNIV MSM DEPT R AVERILL 3515 EB EAST LANSING MI 48824-1226
1	UNIV OF KENTUCKY L PENN 763 ANDERSON HALL LEXINGTON KY 40506-0046
1	UNIV OF WYOMING D ADAMS PO BOX 3295 LARAMIE WY 82071
2	PENN STATE UNIV R MCNITT C BAKIS 212 EARTH ENGR SCIENCES BLDG UNIVERSITY PARK PA 16802
1	PENN STATE UNIV R S ENGEL 245 HAMMOND BLDG UNIVERSITY PARK PA 16801
1	PURDUE UNIV SCHOOL OF AERO & ASTRO C T SUN W LAFAYETTE IN 47907-1282

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	STANFORD UNIV DEPT OF AERONAUTICS & AEROBALLISTICS S TSAI DURANT BLDG STANFORD CA 94305
1	UNIV OF DAYTON J M WHITNEY COLLEGE PARK AVE DAYTON OH 45469-0240
7	UNIV OF DELAWARE CTR FOR COMPOSITE MTRLS J GILLESPIE M SANTARE G PALMESE S YARLAGADDA S ADVANI D HEIDER D KUKICH 201 SPENCER LABORATORY NEWARK DE 19716
1	DEPT OF MATERIALS SCIENCE & ENGINEERING UNIVERSITY OF ILLINOIS AT URBANA CHAMPAIGN J ECONOMY 1304 WEST GREEN ST 115B URBANA IL 61801
1	NORTH CAROLINA STATE UNIV CIVIL ENGINEERING DEPT W RASDORF PO BOX 7908 RALEIGH NC 27696-7908
1	UNIV OF MARYLAND DEPT OF AEROSPACE ENGNRNG A J VIZZINI COLLEGE PARK MD 20742
3	UNIV OF TEXAS AT AUSTIN CTR FOR ELECTROMECHANICS J PRICE A WALLS J KITZMILLER 10100 BURNET RD AUSTIN TX 78758-4497

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
3	VA POLYTECHNICAL INST & STATE UNIV DEPT OF ESM M W HYER K REIFSNIDER R JONES BLACKSBURG VA 24061-0219		<u>ABERDEEN PROVING GROUND (CONT)</u>
1	DREXEL UNIV A S D WANG 32ND & CHESTNUT ST PHILADELPHIA PA 19104		AMSRL WM B A HORST AMSRL WM BA F BRANDON AMSRL WM BC P PLOSTINS D LYON J NEWILL S WILKERSON A ZIELINSKI AMSRL WM BD B FORCH R FIFER R PESCE RODRIGUEZ B RICE AMSRL WM BE C LEVERITT D KOOKER AMSRL WM BR C SHOEMAKER J BORNSTEIN AMSRL WM M D VIECHNICKI G HAGNAUER J MCCAULEY B TANNER AMSRL WM MA R SHUFORD P TOUCHET N BECK TAN AMSRL WM MA D FLANAGAN L GHORSE D HARRIS S MCKNIGHT P MOY P PATTERSON G RODRIGUEZ A TEETS R YIN AMSRL WM MB B FINK J BENDER T BOGETTI R BOSSOLI L BURTON K BOYD S CORNELISON P DEHMER R DOOLEY W DRYSDALE G GAZONAS
1	SOUTHWEST RSCH INST ENGR & MATL SCIENCES DIV J RIEGEL 6220 CULEBRA RD PO DRAWER 28510 SAN ANTONIO TX 78228-0510		
	<u>ABERDEEN PROVING GROUND</u>		
1	US ARMY MATERIEL SYSTEMS ANALYSIS ACTIVITY P DIETZ 392 HOPKINS RD AMXSY TD APG MD 21005-5071		
1	DIRECTOR US ARMY RESEARCH LAB AMSRL OP AP L APG MD 21005-5066		
105	DIR USARL AMSRL CI AMSRL CI H W STUREK AMSRL CI S A MARK AMSRL CS IO FI M ADAMSON AMSRL SL B J SMITH AMSRL SL BA AMSRL SL BL D BELY R HENRY AMSRL SL BG AMSRL SL I AMSRL WM E SCHMIDT		

NO. OF
COPIES ORGANIZATION

ABERDEEN PROVING GROUND (CONT)

AMSRL WM MB
S GHIORSE
D GRANVILLE
D HOPKINS
C HOPPEL
D HENRY
R KASTE
M KLUSEWITZ
M LEADORE
R LIEB
E RIGAS
J SANDS
D SPAGNUOLO
W SPURGEON
J TZENG
E WETZEL
AMSRL WM MB
A FRYDMAN
AMRSL WM MC
J BEATTY
E CHIN
J MONTGOMERY
A WERECZAK
J LASALVIA
J WELLS
AMSRL WM MD
W ROY
S WALSH
AMSRL WM T
B BURNS
AMSRL WM TA
W GILLICH
T HAVEL
J RUNYEON
M BURKINS
E HORWATH
B GOOCH
W BRUCHEY
AMSRL WM TC
R COATES
AMSRL WM TD
A DAS GUPTA
T HADUCH
T MOYNIHAN
F GREGORY
A RAJENDRAN
M RAFTENBERG
M BOTELER
T WEERASOORIYA
D DANDEKAR
A DIETRICH

NO. OF
COPIES ORGANIZATION

ABERDEEN PROVING GROUND (CONT)

AMSRL WM TE
A NILER
J POWELL
AMSRL SS SD
H WALLACE
AMSRL SS SE R
R CHASE
AMSRL SS SE DS
R REYZER
R ATKINSON
AMSRL SE L
R WEINRAUB
J DESMOND
D WOODBURY

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>	<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	LTD R MARTIN MERL TAMWORTH RD HERTFORD SG13 7DG UK	1	ISRAEL INST OF TECHNOLOGY S BODNER FACULTY OF MECHANICAL ENGR HAIFA 3200 ISRAEL
1	SMC SCOTLAND P W LAY DERA ROSYTH ROSYTH ROYAL DOCKYARD DUNFERMLINE FIFE KY 11 2XR UK	1	DSTO MATERIALS RESEARCH LAB NAVAL PLATFORM VULNERABILITY SHIP STRUCTURES & MTRLS DIV N BURMAN PO BOX 50 ASCOT VALE VICTORIA AUSTRALIA 3032
1	CIVIL AVIATION ADMINSTRATION T GOTTESMAN PO BOX 8 BEN GURION INTERNL AIRPORT LOD 70150 ISRAEL	1	ECOLE ROYAL MILITAIRE E CELENS AVE DE LA RENAISSANCE 30 1040 BRUXELLE BELGIQUE
1	AEROSPATIALE S ANDRE A BTE CC RTE MD132 316 ROUTE DE BAYONNE TOULOUSE 31060 FRANCE	1	DEF RES ESTABLISHMENT VALCARTIER A DUPUIS 2459 BOULEVARD PIE XI NORTH VALCARTIER QUEBEC CANADA PO BOX 8800 COURCELETTE GOA IRO QUEBEC CANADA
3	DRA FORT HALSTEAD P N JONES M HINTON SEVEN OAKS KENT TN 147BP UK	1	INSTITUT FRANCO ALLEMAND DE RECHERCHES DE SAINT LOUIS DE M GIRAUD 5 RUE DU GENERAL CASSAGNOU BOITE POSTALE 34 F 68301 SAINT LOUIS CEDEX FRANCE
1	DEFENSE RESEARCH ESTAB VALCARTIER F LESAGE COURCELETTE QUEBEC COA IRO CANADA	1	ECOLE POLYTECH J MANSON DMX LTC CH 1015 LAUSANNE SWITZERLAND
1	SWISS FEDERAL ARMAMENTS WKS W LANZ ALLMENDSTRASSE 86 3602 THUN SWITZERLAND	1	TNO PRINS MAURITS LABORATORY R IJSSELSTEIN LANGE KLEIWEG 137 PO BOX 45 2280 AA RIJSWIJK THE NETHERLANDS

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	FOA NATL DEFENSE RESEARCH ESTAB DIR DEPT OF WEAPONS & PROTECTION B JANZON R HOLMLIN S 172 90 STOCKHOLM SWEDEN
2	DEFENSE TECH & PROC AGENCY GROUND I CREWTHIER GENERAL HERZOG HAUS 3602 THUN SWITZERLAND
1	MINISTRY OF DEFENCE RAFAEL ARMAMENT DEVELOPMENT AUTH M MAYSELESS PO BOX 2250 HAIFA 31021 ISRAEL
1	DYNAMEC RESEARCH AB AKE PERSSON BOX 201 SE 151 23 SODERTALJE SWEDEN
1	TNO DEFENSE RESEARCH I H PASMAN POSTBUS 6006 2600 JA DELFT THE NETHERLANDS
1	B HIRSCH TACHKEMONY ST 6 NETAMUA 42611 ISRAEL
1	DEUTSCHE AEROSPACE AG DYNAMICS SYSTEMS M HELD PO BOX 1340 D 86523 SCHROBENHAUSEN GERMANY

INTENTIONALLY LEFT BLANK.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE May 2001		3. REPORT TYPE AND DATES COVERED Final, June 1998-July 2000
4. TITLE AND SUBTITLE Rapid Automated Induction Lamination (RAIL) for High-Volume Production of Carbon/Thermoplastic Laminates			5. FUNDING NUMBERS PP1109	
6. AUTHOR(S) Nicholas Shevchenko, Bruce K. Fink, Shridhar Yarlalagadda,* John J. Tierney,* Dirk Heider,* and John W. Gillespie, Jr.*				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRL-WM-MB Aberdeen Proving Ground, MD 21005-5069			8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-2478	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Strategic Environmental Research & Development Program Office 901 North Stuart Street Arlington, VA 22203			10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES * Center for Composite Materials, University of Delaware, Newark, DE 19716				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) An innovative Rapid Automated Induction Lamination (RAIL) process has been developed that can fabricate fully consolidated 8-ply AS4/polyetherimide (PEI) laminates in high volumes. The process relies on induction-based rapid volumetric heating for multilayer consolidation at very rapid rates (less than 30-s cycle times), while maintaining high quality (<1% voids). Full translation of mechanical properties has been achieved in comparison to baseline processes, such as autoclave and vacuum debulk with an order of magnitude increase in throughput. The RAIL process has the potential to be integrated with thermoforming for high-volume production of net-shape carbon/thermoplastic parts.				
14. SUBJECT TERMS induction, carbon fiber, thermoplastic composites, high volume, RAIL, composite material			15. NUMBER OF PAGES 40	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED		18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED		19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED
				20. LIMITATION OF ABSTRACT UL

INTENTIONALLY LEFT BLANK.

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number/Author ARL-TR-2478 (Shevchenko) Date of Report May 2001
2. Date Report Received _____
3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT
ADDRESS

Organization

Name

E-mail Name

Street or P.O. Box No.

City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD
ADDRESS

Organization

Name

Street or P.O. Box No.

City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)
(DO NOT STAPLE)

DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS

BUSINESS REPLY MAIL

FIRST CLASS PERMIT NO 0001,APG,MD

POSTAGE WILL BE PAID BY ADDRESSEE

DIRECTOR
US ARMY RESEARCH LABORATORY
ATTN AMSRL WM MB
ABERDEEN PROVING GROUND MD 21005-5069



NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

